



STONETECH® Heavy Duty Grout Sealer

STONETECH Heavy Duty Grout Sealer is designed for cement based grout and protects against oil and water-based stains.

**Globally Proven
Construction Solutions**



FEATURES/BENEFITS

- Heavy duty protection against most stains
- Protects against grout and makes cleaning easier
- Water-based formula
- Interior and Exterior Use

PACKAGING

- 710mL Spray Bottle, 6 units per Case, 600 units per Pallet
- 946mL, 6 units per Case, 600 units per Pallet
- 3.8L 4 units per Case, 160 units per Pallet
- 18.9L 1 unit per Case, 48 units per Pallet

RECOMMENDED SURFACES

- Cement-based grout for natural stone, ceramic and porcelain tile

USES (INTERNAL/EXTERNAL)

- Countertops
- Splashbacks
- Floors
- Walls

MANUFACTURER

LATICRETE Australia Pty Ltd
29 Telford Street
Virginia, QLD 4014 Australia

Telephone: 07 3865 1599
Toll Free: 1800 331 012
Fax: 07 3865 2250
Internet: www.laticrete.com.au

Approximate Coverage

Depending on stone type, texture and porosity; the site conditions at the time of installation; and the method of installation, the following rates of coverage will vary.

- Up to 38 lineal metres/473 mL
- Up to 61 lineal metres/709 mL
- Up to 76 lineal metres/946 mL
- Up to 305 lineal metres/3.8 L
- Up to 1524 lineal metres/18.9 L

Expected Wear

- Up to 5 years on interior surfaces
- Up to 3 years on exterior surfaces

Shelf Life

Factory sealed containers of this product are guaranteed to be of first quality for two (2) years if stored at temperatures $>10^{\circ}\text{C}$ and $<32^{\circ}\text{C}$.

VOC Content

<300 g/L (excluding water) for EPA Purposes

<5 g/L (including water) for U.S. State purposes (Low Solids Coating)

Storage and Handling Instructions

MAY BE HARMFUL IF SWALLOWED. MAY CAUSE EYE, SKIN AND RESPIRATORY IRRITATION. Do not ingest. Avoid contact with eyes and skin. Avoid prolonged exposure to vapors. KEEP OUT OF THE REACH OF CHILDREN. Do not freeze or store above 38°C . Do not mix with other chemicals. Do not release to natural waterways.

Cautions

Consult SDS for more safety information.

- Inhalation: Remove victim to fresh air and keep at rest in a position comfortable for breathing. Get medical attention if any discomfort continues.
- Skin contact: Wash skin with soap and water. Get medical attention if symptoms occur.
- Eye contact: Flush eyes thoroughly with water for at least 15 minutes. Get medical attention if symptoms persist.
- Ingestion: Rinse mouth. Do not induce vomiting. Get medical attention if any discomfort continues.
- Always test in a small inconspicuous area to determine suitability over polished marble, travertine or limestone.

TECHNICAL DATA

Physical Properties

| | |
|--------|--------------|
| Form | Liquid |
| Colour | Cloudy White |
| Odour | Mild |
| pH | 4 |

Working Properties

| | |
|-------------|---------------|
| Full cure | 24 – 48 hours |
| Surface Use | 4 hours |

Specifications subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions.

INSTALLATIONS

Surface Preparation

Read entire label before using. Use only as directed. Test in a small inconspicuous area with a 24 hour cure time to determine ease of application and desired results. Allow new grout installations to cure for at least 72 hours prior to application. Make sure surface is clean, thoroughly dry and free of waxes and coatings. Surface temperature should be 10°C – 27°C . Ensure work area is wellventilated during application and until surface is dry. Keep children and pets out of the area until surface use resumes.

Application

1. Apply STONETECH® Heavy Duty Grout Sealer directly onto grout lines and joints to thoroughly wet surface using a paint pad, roller or brush. Avoid applying sealer on unintended surfaces.
2. Allow sealer to completely penetrate into the grout, 5–15 minutes.
3. Liberally apply a second coat following steps 1–2.
4. Wipe up all sealer from the surface of the tile. Use a clean, dry, lint-free, cotton towel or mop to remove excess sealer.
5. If sealer was not completely wiped off and a residue appears, wipe entire surface with a towel dampened with sealer. Use a white nylon pad to loosen residue and wipe surface with a clean, white absorbent towel.
6. A full cure is achieved after 24-48 hours; surface use may begin in 4 hours. If use of the surface must resume sooner, cover the treated surface with red rosin paper to protect it until full cure is achieved.
7. Clean tools used during application with water.

Cleaning

Clean tools used during application with water.

AVAILABILITY AND COST

Availability

LATICRETE and LATAPOXY® materials are available worldwide.

For Distributor information:

Toll Free: 1800 331 012

Telephone: 07 3865 1599

For online distributor information, visit LATICRETE at www.laticrete.com.au

Cost

Contact a LATICRETE Distributor in your area.

MAINTENANCE

Highly alkaline, acidic, ammoniated or abrasive cleaners are not necessary for daily maintenance and may also degrade the STONETECH ealer used, adversely affecting stain resistance. Tile and stone routine cleaning with a neutral pH cleaner such as STONETECH Stone & Tile Cleaner is recommended. For tough or difficult to remove soil use STONETECH KlenzAll™ Cleaner, a nylon scrubbing pad or a long handled stiff bristle brush. Please note: Prior to using any cleaning material on a tile, stone, etc. installation, test a discrete area or scrap piece of tile to insure desired results

TECHNICAL SERVICES

Technical assistance

Information is available by calling:

Toll Free: 1800 331 012

Telephone: 07 3865 1599

Fax: 07 3865 2250

Technical and safety literature

To acquire technical and safety literature, please visit our website at

www.laticrete.com.au

DISCLAIMER

The information contained in this document is given in good faith and to the best of our knowledge is true and accurate. This information is subject to change without notice and it is the responsibility of the user to obtain up to date and current information. The use of this product is beyond our control and LATICRETE is not responsible for any loss or damage arising from the incorrect use of this product. Efflorescence is a normal condition of Portland cement and is not covered by any warranty.

LATICRETE Australia Pty Ltd

29 Telford Street, Virginia

QLD 4014 Australia

1800 331 012

www.laticrete.com.au