

**LATICRETE® 4237 RAPID LATEX THIN-SET MORTAR ADDITIVE
WITH LATICRETE 211 CRETE FILLER POWDER (or 1:1 PC/Sand)**

Install Tile at Temperature	Ready for Foot Traffic	Ready for Heavy Traffic
45° F (4° C)	12 hours	14 hours
50° F (10° C)	6 hours	8 hours
60° F (16° C)	3-3/4 hours	4 hours
70° F (21° C)	3-1/2 hours	3-3/4 hours
80° F (27° C)	3 hours	3-1/2 hours
90° F (32° C)	2 hours	2-1/2 hours

**LATICRETE 101 RAPID-SET LATEX ADMIX WITH A LATICRETE THIN-SET MORTAR
(LATICRETE 272, 317, 280)**

Install Tile at Temperature	Ready for Foot Traffic	Ready for Heavy Traffic
45° F (4° C)	16 hours	20 hours
50° F (10° C)	12 hours	16 hours
60° F (16° C)	8 hours	12 hours
70° F (21° C)	5 hours	8 hours
80° F (27° C)	5 hours	7 hours
90° F (32° C)	4 hours	6 hours

Technical Data Sheets are subject to change without notice. For latest revision, check our website @ www.laticrete.com
TDS 116.doc R 3 January 2005

LATICRETE, LATAPOXY and the  logo are Registered Trademarks of LATICRETE International, Inc.

